

UNIKING® PC 4310C

特征 Features

PC+10%CF, 无卤阻燃, 高强度
Carbon fiber reinforced Pc resin, 10% by weight. Halogen free flame retardant. High strength.

应用 application

家电、数码产品模组
Household appliances, digital products module

项目 Items	测试方法 Standard	测试条件 Condition	单位 Unit	典型值 Typical Value
物理性能 Physical properties				
比重 Specific Gravity	ISO 1183	---	g/cm ³	1.23
熔融指数 Mass Melt Flow Rate	ISO 1133	300°C/1.2Kg	g/10min	10~18
成型收缩率 Molding Shrinkage	ISO 294	Flow, 3.2mm	%	0.3
		X-flow, 3.2mm	%	0.5
填充含量 Filler content	Internal-method	750°C/2H	%	10
吸水率 Moisture Absorption	ISO 62	24h, 平衡	%	0.2
力学性能 Mechanical properties				
拉伸强度, 屈服 Tensile Strength, Yield	ISO 527	20mm/min	Mpa	95
断裂伸长率, 断裂 Elongation at Break	ISO 527	20mm/min	%	3.5
弯曲强度 Flexural Strength	ISO 178	2mm/min	Mpa	135
弯曲模量 Flexural Modulus	ISO 178	2mm/min	Mpa	4200
悬臂梁缺口冲击强度 Izod Impact, Notched	ISO 180	5.5J, 23°C	KJ/m ²	14
		5.5J, -30°C	KJ/m ²	10
热性能 Thermal properties				
热变形温度 HDT, un annealed	ISO 75	1.8Mpa	°C	127
维卡软化温度 Vicat Softening Temperature	ISO 306	50A	°C	140
线性膨胀系数 CLTE	ISO 11359	-40~40°C	Cm/°C/°C	40*10 ⁻⁶
阻燃性能 Flammability	UL94	1.6mm	Grade	V0
		3.2mm	Grade	V0
电气性能 Electrical properties				
相对介电常数 Relative Permittivity	IEC 60250	1MHz	---	3.2
介电强度 Dielectric Strength	IEC 60243	S/T, in oil	KV/mm	22
功耗因数 Dissipation Factor	IEC 60250	1MHz	---	0.033
体积电阻率 Volume Resistivity	IEC 60112	23°C	ohm•cm	1.0E+16

1)染色料的性能可能与以上数值有不同。所有数据是在 23°C、50%相对湿度的环境中存放48小时后测试所得。除流动指数外的其它性能均使用注塑样条进行测试的。

Variations within normal tolerances are possible for various colors. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt flow rates, are measured on injection molded samples.

2)典型值是指实验平均数据, 仅用于使用时的参考, 不作为产品的标准。

Only typical data for selection purposes. Property values is the average experimental data, when used only for reference, not as a product standards.

加工信息
Processing information

UNIKING® PC 4310C

建议加工条件 Suggested Processes Condition		
干燥温度 Drying Temperature	°C	80~120
干燥时间 Drying Time	H	2~4
建议最大湿含量 Suggested Max Moisture	%	<0.015
后段温度 Rear Temperature	°C	250~280
中段温度 Middle Temperature	°C	250~290
前段温度 Front Temperature	°C	250~310
射嘴温度 Nozzle Temperature	°C	250~310
成型(熔体)温度 Processing(Melt) Temperature	°C	250~300
模具温度 Mold Temperature	°C	60~130
注塑压力 Injection Pressure	Mpa	70~140
注塑速度 Injection Rate		中等速度
背压 Back Pressure	Mpa	0.1~0.3
螺杆转速 Screw Speed	rpm	30~70

以上数值为实验室测得，实际可能会有所不同，可根据不同机型、不同模具以及产品要求，做适当调整。
Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

标准免责声明

根据您的实际需求,使用我们的产品和相关信息(无论是口头、书面或通过生产评估),包括任何建议配比和工艺,是我们无法控制的。因此,重要的是您测试我们的产品、分析信息来决定是否适合你的预期用途和应用。从技术以及健康、安全和环保角度来看,必须通过测试来确定适宜性。所有的信息和技术支持是不做保证或担保的。

Standard Disclaimer

Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

燃烧性能

燃烧性能的结果仅为小规模实验室检测所得,不能反映灾害或任何其他材料在实际火灾中的燃烧情况。

Flammability

Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

安全防护

使用这些产品之前,你必须阅读和熟悉安全与防护方面的信息,了解他们的危害及正确使用和处理。相关信息有材料安全数据表(MSDS)和产品标签。

Health and Safety

Before working with these products, you must read and become familiar with the safety and protection of information on their hazards, proper use, and handling. Relevant information is material safety data sheets (MSDS) and product labels.